



# Lustro

## Metallic Topcoat

### DESCRIPTION

- Trowel or blade applied, high performance epoxy-acrylic hybrid sealer.
- Improves resistance to water, chemicals, stains, scratches and scuffs while adding a metallic shimmer effect.

### USES

- For interior applications over smooth surfaces.
- Seal any smooth Variance® finish.
- Seal other types of plaster or wall finishes.

### COLORS

- Standard colors: refer to Variance® Lustro color chart.

### COMPOSITION

- VOC content: <20 grams per liter
- Meets SCAQMD Rule 1113 when using ParexUSA Non-VOC Colorants.

### COVERAGE

Coverage will vary depending on surface conditions and thickness of application.

- 800-1000 ft<sup>2</sup> (74.3-92.9 m<sup>2</sup>) per gallon (one coat).

### CONTAINER

- 8 lbs (3.6 kg) net weight in 1 gal. plastic pails.
- 2 lbs (.9 kg) net weight in 1 qt. cans.
- Storage: Protect from direct sunlight and keep from freezing.
- Shelf life: Reference ParexUSA Expiration Date of Products Technical Bulletin.

### DRYING TIME

- Avoid, rain heavy traffic or cleaning for 48 hours after application.
- 3-4 hours under normal conditions.
- High humidity and low temperatures extend drying time.

### CLEAN-UP

- Clean tools frequently using clean water prior to drying.

### SURFACE PREPARATION

- Substrate must be clean, dry, sound and free of contaminants such as dust, oil, mildew and efflorescence.
- Ambient conditions, substrate and the product itself must be at a minimum of 40°F during application and at least 48 hours following.

### MIXING

- No mixing or thinning of the product is required.

### APPLICATION

- ParexUSA recommends that the project owner or designer approve a job site mock-up of the application of this product. The mock-up should demonstrate the product's appearance under the conditions given by the project specification(s).
- Periodically, as the work progresses, evaluate it from a distance to ensure the desired effect is being produced across the entire surface.
- May be applied over any smooth Variance® finish.
- For best results, apply using Venetian trowels. Apply Variance® Lustro in very thin, even coats.
- Apply using decorative, multi-directional trowel strokes.
- For maximum protection and for a more even appearance apply in 2 or more coats.
- Allow 2 hours in between coats. Once the surface has dried to the touch it may be burnished slightly with a clean, dry Venetian trowel to increase shine and smoothness.
- Apply a test area in an inconspicuous area to evaluate compatibility. Gloss and satin versions available.

### LIMITATIONS

- Use only on surfaces that are sound, clean, dry, and free from any residue that might affect the ability of this product to bond to the surface.
- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Provide supplemental heat and protection from moisture as needed.
- Application in direct sunlight in hot weather may adversely affect aesthetics.
- Do not allow to freeze until completely dry.
- Always wear proper safety equipment, including particle mask, eye protection and gloves when mixing and/or applying this product
- In case of contact with eyes, flush with clean water and seek medical attention if irritation persists
- Do not use harsh or abrasive cleaners. Wash using a soap and water solution, followed by a warm water rinse. Do not use harsh or abrasive cleaners

### WARNING

- Read complete Warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, ParexUSA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

## PAREXUSA

ParexUSA, Inc.  
4125 E. La Palma Ave., Suite 250  
Anaheim, CA 92807  
www.parexusa.com

866-516-0061 Tech Support: 800-226-2424

CI SOLUTIONS • STUCCO ASSEMBLIES • TILE AND STONE SYSTEMS